

African Pegmatite (Pty) Ltd
 27 Van Der Bijl Street,
 PO Box 598, Meyerton 1960
 Gauteng, South Africa
 Email: wenger@pegmatite.co.za
 reception@pegmatite.co.za
 Website: www.mineralmilling.com

Tel: +27 016 362 0600/1/2/3/4
 Int: +27 16 362 0600
 Fax: 016 362 1239

MILLERS & PROCESSORS OF BASE MINERALS



Approved by:
 Compiled by: J Sowerby

Doc No: DSC 016
 Rev No: 02

Date: 12 February 2008
 Page: 1 of 1

Data Sheet




**Product: Medium Swell Coking
 Grade: Natural Grade**

CHEMICAL ANALYSIS %

Typical:	Ash	11 %	Ro V mean max	0.73 %
	Volatile matter	38 – 40 %	Inherent moisture	3.3 %
	Fixed carbon	53.5 %	Heat value [d.b.]	
	Total sulphur	1.01 %	MJ/kg	29.8
	Phosphorus	0.006 %	Kcal/kg	7115
	Roga Index	73	Hardgrove Index	56
	Swell index	x4	Moisture	2.5 - 3 % max
	FSI	5	AFS	90 - 120

PETROGRAPHIC PROPERTIES:

Vitrinite	87.4 %
Exinite	1.7 %
Reactive semi-fusinite	1.0 %
Total reactives	90.1 %
Inertinite	4.2 %



APPLICATION:

Medium swell coke is used in Green sand foundries, in manual mouldings, Automated castings and plants (Disamatics). Reducing agent

PACKING:

Packed in 3 ply 40kg paper bags or 1 ton bulk bags

The information and recommendations in this product data sheet are based on data we believe to be reliable. They are offered in good faith, but do not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. As such, African Pegmatite Company South Africa makes no express or implied warranties of any kind with respect to this product, including but not limited to any implied warranty of merchantability or fitness for a particular purpose.

We recommend that the user determine whether the products and the information given are appropriate, and that the suitability and performance of our products are appropriate by testing with its own equipment. Specifications are subject to change without notice.

The information and recommendations given in this product data sheet should not be understood as a recommendation for the use of our products in violation of any patent or as a license to use any patents of the African Pegmatite Company South Africa.

Tel: +27 16 362-0600/4 Fax: +27 16 362-1239 Website: www.mineralmilling.com

