African Pegmatite (Pty) Ltd 27 Van Der Bijl Street, PO Box 598, Meyerton 1960 Gauteng, South Africa Email: wenger@pegmatite.co.za reception@pegmatite.co.za Website: www.mineralmilling.com

Tel: +27 016 362 0600/1/2/3/4 Int: +27 16 362 0600 Fax: 016 362 1239

MILLERS & PROCESSORS OF BASE MINERALS



Approved By: EJ Wenger Compiled By: D. Prevoo

Doc No. : DS 022 Rev No. : 05 Date: 05 September 2014

Page 1 of 1

Data Sheet





Product: Iron Pyrites

Grades: ONG

CHEMICAL ANALYSIS %

Typical:	S	47	-	55.0%
	Fe	44.0	-	46.5%
	SiO_2	2.5	-	4.5%
	CaO	0.1	-	0.3%
	Zn	0.1% Max		
	Fe2O3	55	-	64.0%

NB. THIS IS A NATURAL MATERIAL.

PHYSICAL PROPERTIES:

Particle Size: -1mm

Specs: Moisture: 3.0 % Maximum

Colour: Gold

APPLICATION:

Sulphur source for glass colourant, rubber, explosives, Sulphur impregnated compounds and reductant for metal refining.

PACKING:

Packed in 40kg bags on pallets and 1m/t bulk bags.

The information and recommendations in this product data sheet are based on data we believe to be reliable. They are offered in good faith, but do not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. As such, African Pegmatite Company South African makes no express or implied warranties of any kind with respect to this product, including but not limited to any implied warranty of merchantability or fitness for a particular purpose.

We recommend that the user determine whether the products and the information given are appropriate, and that the suitability and performance of our products are appropriate by testing with its own equipment. Specifications are subject to change without notice.

The information and recommendations given in this product data sheet should not be understood as a recommendation for the use of our products in violation of any patent or as a license to use any patents of the African Pegmatite Company South Africa.

Tel: +27 16 362-0600/4 Fax: +27 16 362-1239 Website: www.mineralmilling.com









