



Date: 10 February 2023
Approved by: A. Wenger
Compiled by: D. Prevoo

Pages: 1 of 2
Doc No: DS003
Rev No: 10

DATA SHEET

Chrome Flour
Grade: Export
Use: Colourants, Chemicals, Refractory monolithic and bricks.



Chemical Analysis (%):

Typical:				
Cr2O3	43.5% Typical	44%	MgO	10 - 11%
SiO2		3 - 5%	Al2O3	14 - 15%
CaO		0.5 – 1.0%	Cr/Fe	1 : 1.54
FeO		25 - 26%		

Physical Properties:

Particle Size:	45 µm	- 2-3%
	Moisture	- 0.2% max
Specific Denisty:	4.46 g/cm ³	
Density:	Dry Bulk Density 1700kgs/Cubic Metre	
pH:	9 10% Watermix	
Expansion coefficient:	25°C - 300°C	229.2 x 10 ⁻⁷ Cubical
% < 80 Microns:	300°C - 500°C	240 x 10 ⁻⁷ Cubical
Diameter D50:	Nil – See below Graph	
	8.286 Microns	

Application:

Colourant in glass and ceramics. Refractory monolithics and bricks.
Chemicals

Packaging:

Packed in 25kg or 40kg -3 ply paper bags, stretch wrapped on pallets, or 1m/t polypropylene bags.

*The information and recommendations in this product data sheet are based on data we believe to be reliable. They are offered in good faith, but do not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. As such, African Pegmatite Company South Africa makes no express or implied warranties of any kind with respect to this product, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. We recommend that the user determine whether the products and the information given are appropriate, and that the suitability and performance of our products are appropriate by testing with its own equipment. Specifications are subject to change without notice. The information and recommendations given in this product data sheet should not be understood as a recommendation for the use of our products in violation of any patent or as a license to use any patents of the African Pegmatite Company South Africa.




AFRICAN PEGMATITE

info@pegmatite.co.za
 www.mineralmilling.com
 Tel: +27 (0)16 362 0600
 Fax: +27 (0)16 362-1239

MILLERS AND PROCESSORS OF BASE MINERALS

Date: 10 February 2023
Approved by: A. Wenger
Compiled by: D. Prevoo

Pages: 2 of 2
Doc No: DS003
Rev No: 10



Size (µm)	Vol Under %	Size (µm)	Vol Under %	Size (µm)	Vol Under %	Size (µm)	Vol Under %	Size (µm)	Vol Under %	Size (µm)	Vol Under %
0.020	0.00	0.142	0.00	1.002	9.33	7.096	46.00	50.238	99.01	355.656	100.00
0.022	0.00	0.159	0.00	1.125	10.55	7.962	48.99	56.368	99.69	399.052	100.00
0.025	0.00	0.178	0.00	1.262	11.90	8.934	52.16	63.246	99.97	447.744	100.00
0.028	0.00	0.200	0.02	1.416	13.39	10.024	55.54	70.963	100.00	502.377	100.00
0.032	0.00	0.224	0.15	1.589	15.04	11.247	59.13	79.621	100.00	563.677	100.00
0.036	0.00	0.252	0.38	1.783	16.84	12.619	62.91	89.337	100.00	632.456	100.00
0.040	0.00	0.283	0.72	2.000	18.79	14.159	66.85	100.237	100.00	709.627	100.00
0.045	0.00	0.317	1.16	2.244	20.88	15.887	70.90	112.468	100.00	796.214	100.00
0.050	0.00	0.356	1.69	2.518	23.09	17.825	74.96	126.191	100.00	893.367	100.00
0.056	0.00	0.399	2.30	2.825	25.39	20.000	78.97	141.589	100.00	1002.374	100.00
0.063	0.00	0.448	2.98	3.170	27.78	22.440	82.81	158.866	100.00	1124.683	100.00
0.071	0.00	0.502	3.72	3.557	30.23	25.179	86.39	178.250	100.00	1261.915	100.00
0.080	0.00	0.564	4.51	3.991	32.71	28.251	89.61	200.000	100.00	1415.892	100.00
0.089	0.00	0.632	5.35	4.477	35.24	31.698	92.42	224.404	100.00	1588.656	100.00
0.100	0.00	0.710	6.24	5.024	37.82	35.566	94.76	251.785	100.00	1782.502	100.00
0.112	0.00	0.796	7.20	5.637	40.45	39.905	96.62	282.508	100.00	2000.000	100.00
0.126	0.00	0.893	8.22	6.325	43.17	45.000	98.08	316.979	100.00		

*The information and recommendations in this product data sheet are based on data we believe to be reliable. They are offered in good faith, but do not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. As such, African Pegmatite Company South Africa makes no express or implied warranties of any kind with respect to this product, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. We recommend that the user determine whether the products and the information given are appropriate, and that the suitability and performance of our products are appropriate by testing with its own equipment. Specifications are subject to change without notice. The information and recommendations given in this product data sheet should not be understood as a recommendation for the use of our products in violation of any patent or as a license to use any patents of the African Pegmatite Company South Africa.